

MELLOR BUFF MULTI

PRODUCT INFORMATION



www.brickability.co.uk

0870 143 3332

Queensgate House, Cookham Road, Bracknell, Berkshire RG12 1RB

Issue Date: March 2024

Packaging	Shrink-Band
-----------	-------------

TECHNICAL INFORMATION

Brick Dimensions (L x W x H)	215 x 102 x 65mm
Size Tolerances Mean & Range	T2, R1
Configuration	Perforated
Voids	18-25%
Mean Compressive Strength	≥30 N/mm ²
Active Soluble Salts	S2
Water Absorption	≤20%
Durability	F2
Gross Dry Density	NPD Kg/m ³
Equivalent Thermal Conductivity	NPD W/ mK
Initial Rate of Absorption	NPD Kg/(m ² min)