


USK

PRODUCT INFORMATION



Packaging	Shrink wrapped & Palletised
-----------	-----------------------------

TECHNICAL INFORMATION

Brick Dimensions (L x W x H)	215 x 102 x 65mm
Size Tolerances Mean & Range	T1, R1
Configuration	Perforated
Voids	≤ 37%
Mean Compressive Strength	≥40 N/mm ²
Active Soluble Salts	S2
Water Absorption	≤6%
Durability	F2
Gross Dry Density	1400 Kg/m ³
Equivalent Thermal Conductivity	0,35 W/ mK
Initial Rate of Absorption	0,6 Kg/(m ² min)

Issue Date: May 2022