

Facing Brick Technical Information Sheet

Carlton

Brown Sandfaced

Configuration:	Vertically Perforated Clay Facing Brick		
Size:	215 x 102.5 x 73 mm		
Dimensional Tolerance:	T2	Dimensional Range:	R1
Density - Net:	2100 kg/m ³	Density (Net) - Tolerance:	D
Density - Gross:	1500 kg/m ³	Density (Gross) - Tolerance:	D
Compressive Strength:	40 N/mm ²	Compressive Strength Category:	II
Water Absorption:	10.0 %		
Soluble Salts Category:	S2		
Durability:	F2		
Thermal Conductivity P=50:	0.62 W/m.K		
Thermal Conductivity P=90:	0.69 W/m.K		
Water Vapour Permeability Coefficient:	50/100		
Dangerous Substances:	N/A		

Bricks are manufactured and supplied to relevant clauses of EN 771-1
Declarations of Performance, Environmental and other policies can be found on the company website:
www.mbhplc.co.uk

Further information is available through our sales department.
Tel: 0844 9310022 email: sales@mbhplc.co.uk