

ASCOT

PRODUCT INFORMATION



www.brickability.co.uk

0870 143 3332

Queensgate House, Cookham Road, Bracknell, Berkshire RG12 1RB

Issue Date: December 2023

Packaging	Shrink wrapped & Palletised
-----------	-----------------------------

TECHNICAL INFORMATION

Brick Dimensions (L x W x H)	215 x 102 x 65mm
Size Tolerances Mean & Range	T2, R1
Configuration	Frogged
Voids	NPD
Mean Compressive Strength	$\geq 12.5 \text{ N/mm}^2$
Active Soluble Salts	S2
Water Absorption	$\leq 16\%$
Durability	F2
Gross Dry Density	1850 Kg/m^3
Equivalent Thermal Conductivity	NPD
Initial Rate of Absorption	$1.5\text{-}4.0 \text{ Kg}/(\text{m}^2\cdot\text{min})$