

Product name Product		group	Production location
Wickford	L1		Lanklaar
he raw materials are excavated in Weichsel loam layers, the nainly consists of a silt-like fraction, suited ideally for the ma urface covering, the desired colour is achieved.	e local loam of Aeoliar anufacturing of hand f	n origin dating fro form bricks. By us	om the Ice Age. This löss sing specific sand types for
	Colour		
ed brown facing brick with dark shades.			
	Format		
Moulding method Hand form			
DF: 214 x 101 x 65 mm Between batches the		average size and color may slightly differ.	
Essential Char	racteristics - EN771-1		
CE EN 771-1 - CPR-97884 NOBC 0063 (ex 0620)		UK CA EN 771 - 1855-CPR-24914	
2+		2+	
Dimensional tolerances	T2		
Range	R1		
Active Soluble Salts	S2		
Mean Compressive strength	>= 20 N/mm ²	20 N/mm ² Tested to the bed face	
Normalized Compressive strength	>= 20 N/mm ²	Tested to the bed face	
Dimensional stability	NPD		
Bond Strength general	0,15 N/mm²	0,15 N/mm²	
Bond Strength thin layer	0,30 N/mm²		
Reaction to fire	A1	Category	
Water absorption	<= 14% m/md		
Water vapour permeability	5/10		
Net dry density	1740 kg/m³ (D1)		
Gross dry density	1630 kg/m³ (D1)		
Thermal conductivity Lambda 50/50	<=0,60 W/m.K		
Durability against freeze thaw	F2		
Dangerous substances	NL-BSB	NL-BSB According to Annex ZA 3	
Other	Characteristics		
Initial rate of water absorption - Non-coated Bricks	1,5 - 4.0 kg/m².min (IW3)	Value according	g EN771-1:2011 - 5.3.8
Initial rate of water absorption - Coated bricks	0,5 - 1,5 kg/m².min (IW2)		
Freeze/thaw resistance - PTV 23-002	NPD	NPD NBN 27-009	
Thermal conductivity Lambda 90/90	0,65 W/m.K		
Thermal conductivity Lambda Ui	0,697 W/m.K		
Thermal conductivity Lambda Ue	1,376 W/m.K		

